



PRODUCT DATA

3/16" Nomex / Aramid

- Continuous to 400 F (204 C)
- High Tensile Strength
- Good Abrasion Resistance
- Excellent Resistance to Solvents
- 1000' Per spool

3/16" Fiberglass with Fiberglass core

- Continuous to 1000 F (538 C)
- Smooth Finish
- High Tensile Strength
- 1000' per spool

3/16" Polyester with Fiberglass Core

- Continuous to 275 F (135 C)
- Melts at 500 F (260 C)
- Non Stretching
- Soft and Flexible for easy tying
- 1000' per spool

¼" Solid Braid Polyester (no core)

- Continuous to 275 F (135 C)
- Melts at 500 F (260 C)
- No Stretch
- 1000' per spool

This information is given in good faith and is believed to be accurate. This information is provided as a specification guide only. No specific Warranties are expressed or implied. It is the purchasers' responsibility to ensure the suitability for use of this product for their specific application.