



VentureClad™ Insulation Jacketing Tapes 1577 Series:

1577CW • 1577CW-E • 1577CW-CM • 1577CW-BM •
1577CW-WM • 1577CW-WME

Technical Data

February, 2017

Product Description 3M™ VentureClad™ Insulation Jacketing System is a zero permeability, all weather, multi-layered laminate coated with an aggressive cold weather acrylic adhesive. Superior resistance to weathering, fungi, UV and extreme environmental conditions. Designed for use as a vapor barrier for insulation cladding and jacketing applications. Available in both flat and embossed.

Features

- Superior adhesion in cold or hot and humid conditions temperatures.
- Bonds and seals at temperatures as cold as -10°F (-23°C)
- Zero permeability, absolute vapor barrier for insulation cladding and jacketing applications
- High puncture and tear resistant
- Flexible and strong
- Cuts and installs easily on-site, no special tools required.
- LEED Compliant.
- Available in multiple colors.

3M™ VentureClad™ Insulation Jacketing

Tapes 1577 Series:

1577CW • 1577CW-E • 1577CW-CM • 1577CW-BM •
1577CW-WM • 1577CW-WME

**Typical
Physical
Properties**

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Product	1577CW	1577CW-E	1577CW-CM	1577CW-BM	1577CW-WM	1577CW-WME
Color	Natural Aluminum	Natural Aluminum	Natural Aluminum	Black	White	White
Embossed	No	Yes	No	No	No	Yes
Total Product Thickness (without Liner)	6.2 mils (0.16mm)	9.0 mils (0.23mm)	8.0 mils (0.20mm)	7.0 mils (0.18mm)	7.0 mils (0.18mm)	9.0 mils (0.23mm)
Peel Adhesion	75 oz/in (21.0 N/25mm)	83 oz/in (23.0 N/25mm)	65 oz/in (18.0 N/25mm)	69 oz/in (19.0 N/25mm)	80 oz/in (22.0 N/25mm)	82 oz/in (23.0 N/25mm)
Tensile Strength	81 lb/in (360 N/25mm)	74 lb/in (329 N/25mm)	69 lb/in (312 N/25mm)	113lb/in (503 N/25mm)	108 lb/in (480 N/25mm)	93 lb/in (414 N/25mm)
Elongation	64%	45%	80%	80%	62%	35%
Service Temperature	-94° to 300°F (-70° to 149°C)	-94° to 300°F (-70° to 149°C)	-94° to 248°F (-70° to 120°C)	-94° to 248°F (-70° to 120°C)	-94° to 248°F (-70° to 120°C)	-94° to 248°F (-70° to 120°C)
Puncture	56 lbs (249N)	54 lbs (240N)	35 lbs (155N)	69 lbs (307N)	60 lbs (267N)	66 lbs (294N)
Emittance	0.03	0.03	N/A	0.84	0.8	0.82
WVTR	0.00 perm	0.00 perm	0.00 perm	0.00 perm	0.00 perm	0.00 perm
Chemical Resistance	Good	Good	Excellent	Excellent	Excellent	Excellent

3M™ VentureClad™ Insulation Jacketing

Tapes 1577 Series:

1577CW • 1577CW-E • 1577CW-CM • 1577CW-BM •

1577CW-WM • 1577CW-WME

Classifications

Product	1577CW	1577CW-E	1577CW-CM	1577CW-BM	1577CW-WM	1577CW-WME
ASTM E84 Flame/Smoke Rating			25/30	25/50	25/45	25/45
UL723 Classified Flame/Smoke Rating (UL file #R10984)	25/25	25/25				
CAN/ULC S102 Classification Flame/Smoke Rating	25/25	25/25			25/25	
Meets FDA Compositional requirements for indirect food contact (21 CFR 175.105 and 21CFR175.125; FDA: Indirect Food Additives: Adhesives and Components of coatings)					X	X
Approved by Canadian Food Inspection Agency for use in food processing facilities as vapor barrier for insulation cladding and jacketing					X	X
Contains Mold Inhibiting Agents	X	X				
Passes ASTM C1338 Fungi Resistance Testing	X	X	X	X	X	X
U.S. Coast Guard Approval	164.112/63/0	164.112/63/0			164.112/1121/WC L MED029OTE	164.112/1121/WC L MED029OTE
IMO Resolution A653 (16)	X	X			X	X
IMO Resolution MSC61 (67) Annex 2 IMO Resolution MSC 61 (67) Annex 1 Part 2 and Annex 2	X	X			X	X
BS476 parts 6 & 7 Class "O"	X	X				
DIN 4102-1	X	X				
SANS 10177 Opart 3 Class 1	X	X				
NYC MEA	X	X				
Meets CINI 3.3-12 Requirement	X	X				
Japan Building Standard Law Article 2, Clause 9	X	X				

3M™ VentureClad™ Insulation Jacketing

Tapes 1577 Series:

1577CW • 1577CW-E • 1577CW-CM • 1577CW-BM •
1577CW-WM • 1577CW-WME

Physical and Chemical Stability

Membrane Version Only 1577CW-CM, 1577CW-BM, 1577CW-WM, 1577CW-WME

Acids	Acetic acid (all concentrations) 50% formic acid 10% hydrochloric acid 30% hydrochloric acid 10% and 35% hydrofluoric acid 10% nitric acid 65% and 100% nitric acid 30% and 85% phosphoric acid 20% sulphuric acid Sulphur dioxide gas, dry 80% and above sulphuric acid	Resistant Resistant Resistant Partially resistant Resistant Resistant Not resistant Resistant Partially resistant Resistant Not resistant
Aldehydes	Acetaldehyde Formaldehyde	Resistant Resistant
Aqueous Alkaline Solutions	Ammonium hydroxide Calcium hydroxide Sodium hydroxide	Not resistant Partially resistant Not resistant
Chlorinated Hydrocarbons	Carbon tetrachloride Chlorinated biphenyls Chloroform Trichloroethylene	Partially resistant Partially resistant Resistant Resistant
Esters	Ethyl acetate	Resistant
Hydrocarbons	Aliphatic hydrocarbons Benzene Gasoline (petrol) Mineral oils Toluene Xylene	Resistant Resistant Resistant Resistant Resistant Resistant
Miscellaneous Substances	Chlorine Hydrogen peroxide Oxygen Water*	Resistant Resistant Resistant Resistant
Other Organic Solutions	Acetone Diethyl ether Nitrobenzene Phenol	Resistant Resistant Not resistant Not resistant
Salt Solutions	Alkaline carbonates Bichromates Cyanides Fluorides	Resistant Resistant Resistant Resistant

*Chemical resistance information based in part on independent test data.

3M™ VentureClad™ Insulation Jacketing

Tapes 1577 Series:

1577CW • 1577CW-E • 1577CW-CM • 1577CW-BM •
1577CW-WM • 1577CW-WME

Storage

Store in a clean, dry place. Temperature of 40-80°F (4-26°C) and 40 to 50% relative humidity are recommended.

Shelf Life

To obtain best performance, use this product within 12 months from date of manufacture

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.



Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
800-362-3550 • 877-369-2923 (Fax)
www.3M.com/construction



Recycled Paper
40% pre-consumer
10% post-consumer

3M and VentureClad are trademarks of 3M Company.
Printed in U.S.A.
©3M 2017 All rights reserved.